



# Unifilo<sup>®</sup> for Closed Molds

### U614, U801, U809, U812, U813, U814, U816, U817, U822, U850, U852, U854

## PRODUCT DESCRIPTION

Unifilo<sup>®</sup> is an Advantex<sup>®</sup> glass continuous filament mat consisting of randomly oriented strands in multiple layers held together with a suitable binder and with a silane coupling agent. The Advantex<sup>®</sup> glass fiber combines the electrical and mechanical properties of traditional E-glass with the acid corrosion resistance of E-CR glass.

- U801 can be used for:
  - parts produced by foaming polyurethane, at low density
  - complex parts molded at low pressure
- U809 is especially suited for Polyurethane foam reinforcement and widely used in LNG carrier thermal insulation
- U614, U812, U813, U814, U816, U817, U822, can be used for:
  - parts molded by RTM, L-RTM, infusion or wet compression with UP, VE, EP and PU resins
  - gypsum parts with improved fire resistance and mechanical properties
- U850, U852, U854 are suited especially for molding with highly filled resins. Super performances met by infusion thanks to the core in 50 tex.



© Istock 2009

## PRODUCT REFERENCE

Example : U850 450 – 138

- U : Continuous strand mat (Unifilo<sup>®</sup>)
- 850 : Product classification code
- 450 : Nominal weight per unit area (g/m<sup>2</sup>)
- 138 : Roll width (cm)

## FEATURES AND PRODUCT BENEFITS

- |  |  |
|--|--|
| • U614(*): closed molds mat                          | • Easy unrolling, cutting and handling               |
| • U801: low binder content                           | • Good adaptability to complex shapes                |
| • U809: very low binder content                      | • Even dispersion in PU matrix during foam expansion |
| • U812 to U822: rising binder content and rigidity   | • Easy unrolling, cutting and handling               |
| • U850, U852, U854: core made with higher strand tex | • Outstanding resin flow                             |

(\*) Advantex<sup>®</sup> glass / Available only for NA Market

## TECHNICAL CHARACTERISTICS (NOMINAL VALUES)

REF.	SIZING	BINDER TYPE	SOLUBILITY IN STYRENE	LINEAR WEIGHT OF BASIC STRANDS (TEX)	LOSS ON IGNITION (%)	MOISTURE CONTENT (%)
				Iso 1889	Iso 1887	Iso 3344
U614	Silane	Polyester	Low	36	4.5	< 0.15
U801				25	1.6	< 0.15
U812				25	2.2	< 0.15
U822				25	2.0	< 0.15
U813				25	3.5	< 0.15
U814				25	4	< 0.15
U816				25	6	< 0.15
U850				25/50/25	6	< 0.15
U852				25/50/25	2.5	< 0.15
U854				25/50/25	4	< 0.15
U809				25	0.9	< 0.15
U817				25	7	< 0.15

# Unifilo® for Closed Molds

U614, U801, U809, U812, U813, U814, U816, U817, U822, U850, U852, U854

## VISUAL CHARACTERISTICS OR POSSIBLE DEFECTS

Type A: coarse strands

Type B: cluster of glass fiber

Type C: water spots

Type D: binder spots, dirt and foreign matters (diameter below 30 mm)

Type E: hole

Maximum number of defects allowed: each 100 lm Unifilo® roll section may contain at most 5 of the above listed defects.

## PRODUCT AVAILABILITY

Available widths from 50 to 300 cm

ROLL WIDTH (cm)	STANDARD WEIGHTS (g/m <sup>2</sup> )	APPROXIMATE DIMENSIONS OF FULL* ROLL, 100 CM WIDE <full roll>: a roll having a guaranteed length of at least 90% of the value indicated above.												
		Diameter (cm)		Nominal length (m)										
				U801	U812 U822	U813 U814	U816 U817	U850	U854	U852	U809	U614		
100	100	55			600									
	150				360									
	225		235	250	250	260	270	250	260					
	300		190	200	205	210	220	205	210					
	450		125	130	135	140	155	135	140					
	600		80	85	90	90	100	90	95					
	900		65	70	75	75	85	75	75					
			Nominal weight (kg)											
100	100	55			60									
	150				54									
	225		52	57	57	59	61	57	59					
	300		57	60	62	63	66	62	63					
	450		56	59	61	63	70	61	63	56				
	600		48	51	54	57	63	54	57	51				
	900		59	63	78	68	77	78	68					

## PACKAGING

- Each roll of Unifilo® is wound up onto a cardboard tube of 0.7 kg/m with 103 mm internal diameter, then individually wrapped with a transparent protective film.
- Pallet type:
  - Rolls ≤ 205 cm width: standard pallet (vertical rolls 14 x 114cm)
  - Rolls > 205 cm width: wooden crate (horizontal rolls).
- Pallet protection:
  - Standard pallet = shrink-wrapped (cardboard base and cover)
  - Wooden crate = each roll packaged in a polyethylene bag.

## LABELING

- Each roll carries an information label with product reference.
- Each pallet carries also an information label with: product reference, gross and net weights, the number of rolls on the pallet and their net weight.

## STORAGE

Unifilo® mat must be stored in its original packaging in a place with no humidity and heat. The best conditions are temperatures between 15 and 35°C and a relative humidity level between 35 and 85%. If the product is stored at lower temperature (below 15°C), we recommend to condition it inside the workshop for at least 24 hours prior using, to prevent condensation.

On site stacking of pallets is possible on (1/1) only. Please use a plywood plank between the two pallets to avoid damage the lower pallet.

Contact

Unifilo.ocvamericas@owenscorning.com

Unifilo.ocvemea@owenscorning.com

Unifilo.ocvap@owenscorning.com



## OCV™ Reinforcements

**OWENS CORNING COMPOSITE MATERIALS, LLC**  
ONE OWENS CORNING PARKWAY  
TOLEDO, OHIO 43659  
1.800.GET.PINK™  
www.owenscorning.com  
www.ocvreinforcements.com

**EUROPEAN OWENS CORNING FIBERGLAS, SPRL.**  
166, CHAUSSÉE DE LA HULPE  
B-1170 BRUSSELS  
BELGIUM  
+32.2.674.82.11

**OWENS CORNING - OCV ASIA PACIFIC SHANGHAI REGIONAL HEADQUARTERS**  
2F OLIVE LVO. MANSION  
620 HUA SHAN ROAD  
SHANGHAI 200040  
CHINA  
+86.21.62489922

This information and data contained herein is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.